

H630 CSM

black | density 1.30 | hardness 60

03/07/2014

CSM 60 SHEETING: FOR TECHNICAL APPLICATIONS

FEATURES

High grade chlorosulphonated polyethylene (CSM).

ADVANTAGES

- ▶ Good resistance to diluted and low oxidant acids
- ▶ Excellent oxidation, weather and ozone resistance
- ▶ Very good high temperature resistance
- ▶ Excellent resistance to hydrocarbonated solvents
- ▶ Resistant to alcohols and most inorganic chemical products
- ▶ Moderate resistance to aliphatic and aromatic hydrocarbons
- ▶ Matte finish to guarantee a good surface finished quality, to secure an easy unrolling, and to facilitate adhesive bonding processes

BENEFITS

- ▶ Performance
- ▶ Service life
- ▶ Safety

APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general purpose applications in contact with:

- ▶ water
- ▶ diluted and low oxidant acids

www.trelleborg.com/elastomerlaminates

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

Measured characteristics		Standard	Value	
MECHANICAL				
<i>Rubber compound</i>			CSM	
<i>Density</i>			1.30 ± 0.05	g/cm ³
<i>Hardness</i>		ASTM D2240	60 ± 5	Shore A
<i>Tensile strength</i>		ISO 37	≥ 9	MPa
<i>Elongation at break</i>		ISO 37	≥ 350	%
<i>Tear resistance</i>		ISO 34-1	≥ 20	N/mm
<i>Compression set after 22 h at 70 °C</i>		ISO 815-1	≤ 35	%
TEMPERATURE				
<i>Working temperature</i>			-35/+125	°C
AGEING				
<i>Δ Hardness after 168 h at 70 °C</i>		ASTM D573	≤ 5	Shore A
<i>Ozone resistance, 200 pphm, 48 h, 30 °C, 20 %</i>		ASTM D1149 type A	No crack	
OIL RESISTANCE				
<i>Oil IRM 903, Δ volume after 70 h at 70 °C</i>		ASTM D471	≤ 40	%
CHEMICAL RESISTANCE				
<i>Diluted acids and bases</i>		<i>Concentrated acids and bases</i>	<i>Ozone</i>	<i>Oils and hydrocarbons</i>
Very good		Good	Very good	Good

DIMENSIONS

Thickness (mm)		Width (mm)		Length (m)		Weight (kg/m ²)	Pattern
2	± 0.3	1400	± 2 %	15	± 2 %	2.60	2 sides matt
3	± 0.3	1400	± 2 %	10	± 2 %	3.90	2 sides matt
4	± 0.4	1400	± 2 %	10	± 2 %	5.20	2 sides matt
5	± 0.4	1400	± 2 %	10	± 2 %	6.50	1 side smooth/1 side matt
6	± 0.5	1400	± 2 %	10	± 2 %	7.80	1 side smooth/1 side matt

IDENTIFICATION

<i>Branding</i>	Without.
<i>Packaging</i>	Thickness ≤ 6 mm rolled on cardboard tube Ø 80 mm. Thickness > 6 mm in roll.
<i>Wrapping</i>	Black polyethylene film.
<i>Labelling</i>	Self-adhesive label indicating product name, dimensions, area in m ² , nominal weight, and product code to allow product traceability.